polymer **206** and a common electrode disposed on the bottom side (not shown). Each electrode **202***a*-*g* resembles a letter, as shown.

[0100] Actuation of an active area corresponding to each electrode 202a-g causes surfaces features 210 on surface 204 to become visible. FIG. 3E illustrates actuation of one letter. More specifically, actuation of an active area corresponding to electrode 202a causes the letter 'a' to increase in planar size and depress into polymer 206 corresponding to the thinning of polymer 206, thus creating an electrode surface feature 210a below the polymer thickness. In addition, actuation of an active area corresponding to electrode 202a causes the letter 'a'-shaped electrode 202a to increase in planar size and forces polymer 206 bordering the expanded electrode 202a to elevate and create a ridge polymer surface feature 212a about the electrode 202a. Electrode 202a is thus configured in surface area to affect a surface shape for recessed electrode surface feature 210a and elevated surface feature 212a.

[0101] Electrodes 202a-g and their corresponding active areas and surfaces features may be independently controlled. Thus, in conjunction with suitable control electronics, electrodes 202a-c and their respective active areas and surface features may be actuated simultaneously to create polymer surface features that spell a word. Other letters may be patterned to create customized visual words and outputs.

[0102] The present invention is not limited to simple square or rectangular geometric shapes. Other shapes (circles, triangles, etc.) or complex patterns may be generated with the present invention. For instance, electrodes may be patterned for logos, line drawings, etc. In another embodiment the squares of FIG. 3A may be individually patterned and controlled to generate different surface feature outputs.

[0103] FIG. 3F illustrates a side view of grid surface features for a transducer 260 in accordance with another specific embodiment of the present invention. A non-compliant electrode 262 is mounted to a rigid structure 264. A passive layer 266 is mounted on top surface of polymer 268. On a top surface of polymer 268 is a grid of thin conductive strips 270, such as a metal wires. When polymer 268 is actuated, the conductive wires 270 cut into polymer 268 causing polymer 268 to bulge around the wires 270. Bulging surface polymer features 269 in polymer 268 cause corresponding bulging surface features 267 in passive layer 266. For instance, in one embodiment, the metal wires 270 are laid out in a grid in a diamond pattern like a quilt and when the polymer 268 is actuated the passive layer 266 exhibits a quilted pattern on the surface of passive layer 266.

5. MULTIFUNCTIONALITY

[0104] Electroactive polymers may convert between electrical energy and mechanical energy in a bi-directional manner. Sensing electrical properties of an electroactive polymer transducer also permits sensing functionality.

[0105] FIGS. 1A and 1B may be used to show one manner in which the transducer portion 10 converts mechanical energy to electrical energy. For example, if the transducer portion 10 is mechanically stretched by external forces to a thinner, larger area shape such as that shown in FIG. 1B, and a relatively small voltage difference (less than

that necessary to actuate the film to the configuration in FIG. 1B) is applied between electrodes 14 and 16, the transducer portion 10 will contract in area between the electrodes to a shape such as in FIG. 1A when the external forces are removed. Stretching the transducer refers to deflecting the transducer from its original resting position—typically to result in a larger net area between the electrodes, e.g. in the plane defined by directions 18 and 20 between the electrodes. The resting position refers to the position of the transducer portion 10 having no external electrical or mechanical input and may comprise any pre-strain in the polymer. Once the transducer portion 10 is stretched, the relatively small voltage difference is provided such that the resulting electrostatic forces are insufficient to balance the elastic restoring forces of the stretch. The transducer portion 10 therefore contracts, and it becomes thicker and has a smaller planar area in the plane defined by directions 18 and 20 (orthogonal to the thickness between electrodes). When polymer 12 becomes thicker, it separates electrodes 14 and 16 and their corresponding unlike charges, thus raising the electrical energy and voltage of the charge. Further, when electrodes 14 and 16 contract to a smaller area, like charges within each electrode compress, also raising the electrical energy and voltage of the charge. Thus, with different charges on electrodes 14 and 16, contraction from a shape such as that shown in FIG. 1B to one such as that shown in FIG. 1A raises the electrical energy of the charge. That is, mechanical deflection is being turned into electrical energy and the transducer portion 10 is acting as a generator.

[0106] In some cases, the transducer portion 10 may be described electrically as a variable capacitor. The capacitance decreases for the shape change going from that shown in FIG. 1B to that shown in FIG. 1A. Typically, the voltage difference between electrodes 14 and 16 will be raised by contraction. This is normally the case, for example, if additional charge is not added or subtracted from electrodes 14 and 16 during the contraction process. The increase in electrical energy, U, may be illustrated by the formula U=0.5 Q^2/C , where Q is the amount of positive charge on the positive electrode and C is the variable capacitance which relates to the intrinsic dielectric properties of polymer 12 and its geometry. If Q is fixed and C decreases, then the electrical energy U increases. The increase in electrical energy and voltage can be recovered or used in a suitable device or electronic circuit in electrical communication with electrodes 14 and 16. In addition, the transducer portion 10 may be mechanically coupled to a mechanical input that deflects the polymer and provides mechanical energy.

[0107] Electroactive polymers of the present invention may also be configured as a sensor. Generally, an electroactive polymer sensor detects a "parameter" and/or changes in the parameter. The parameter is usually a physical property of an object such as strain, deformation, velocity, location, contact, acceleration, vibration, pressure, size, etc. In some cases, the parameter being sensed is associated with a physical "event". The physical event that is detected may be the attainment of a particular value or state for example. An electroactive polymer sensor is configured such that a portion of the electroactive polymer deflects in response to the change in a parameter being sensed. The electrical energy state and deflection state of the polymer are related. The change in electrical energy or a change in the electrical impedance of an active area resulting from the deflection may then be detected by sensing electronics in electrical